

---

Date Generated: 20.05.24

## B36 Product Data Sheet

### Material Details

---

<b>Grade:</b>	B36. (Type: Glass Based Laminates - SRBG)
<b>Description:</b>	Epoxy Glass. Superior epoxy glass laminate
<b>Comments:</b>	A high strength Class F rigid insulation with many uses ranging from slot wedges in small motors to major components in turbo-alternators and electronic applications. B36 has excellent electrical and mechanical properties, good dimensional stability and machines well.
<b>Specifications:</b>	BSEN60893-3-2-EPGC203 (Which supersedes BS3953 EP5). The closest NEMA equivalent to this specification is NEMA G11.
<b>Body Colour:</b>	Pale Green
<b>Cover Colour:</b>	Pale Green
<b>Standard Finish:</b>	Satin/Glossy
<b>Size:</b>	1220 x 1220 Thickness Range: 0.4 - 100.0 †

### Typical Applications

---

- Terminal Boards and Tag Strips
- Slot Wedges
- Precision Machined Parts
- Pipeline Insulation
- Phase Barriers
- PCB Electronics Assembly
- Mechanical Applications
- Jigs and Fixtures
- Insulating Bushes Spacers Sleeves
- High Temperature Components
- Electromechanical Components
- Cryogenic Resistance Components
- Bolt Insulation

### General Properties

---

Property	Unit of measure	Typical Value
Density	g/cm <sup>3</sup>	1.9
Water Absorption	mg	10

‡ Where relevant, the flammability test method is used solely to control and monitor consistency of production. Under no conditions should the results be considered in relation to fire hazards under actual conditions of use.

## Electrical Properties

Property	Unit of measure	Typical Value
IR (24hrs Water Immersed)	G □	30000
Electric Strength (Flat Rapid)	kV/mm	17
Breakdown Voltage (Edge Step by Step)	kV	82
Relative Permittivity @ 1 MHz	-	4.8
Dissipation Factor @ 1 MHz	-	0.02
Tracking Index	V	220

## Mechanical Properties

Property	Unit of measure	Typical Value
Flexural Strength	MPa	460
Flexural Strength at 150°C	MPa	290
Impact (Notched CHARPY)	kJ/m2	90

## Thermal Properties

Property	Unit of measure	Typical Value
Thermal Rating Continuous	°C	155
Thermal Rating Intermittent	°C	165

## Notes

- Datasheet Issue No. 4

Disclaimer: The above values are based upon routine test data and do not form the basis of a supply contract. These products may be used in a diverse range of applications and whilst every effort is made to ensure the information in this data sheet is accurate, it must be stressed that it is the user's responsibility to ensure suitability for the intended end use.

Source: <https://www.attwater.com/products/b36/>